15-45 µm Powder
TI CP

CHEMICAL COMPOSITION

	Fe	O	N	C	H	Ti
% max.	**0.08**	**0.17**	**0.03**	**0.03**	**0.01**	**Solde**

ADVANTAGES

Excellent flowability
Plasma atomized powder
High-purity material
Spherical morphology

MORPHOLOGY

Spherical
ISO 9276-06:2008

GRAIN SIZE

By laser diffraction ASTM B822			
	D10	**D50**	**D90**
µm	**12**	**20**	**35**

DENSITY

Tap density - g/cm³	
ASTM B527	**≥ 2.70**

Apparent density - g/cm³	
ASTM B212	**≥ 2.30**

FLOWABILITY

Hall test - s/50g	
ASTM B213	**≤ 32**

This document is not contractually binding. The figures shown are typical values. For information purposes only.

CONTACT
(+33) 4 72 14 55 00
acnis-group.com

ACNIS INTERNATIONAL RCS LYON 803 981 364 // BERNARD CERVOS SOCIETE RCS LYON 380 988 543 // AERO METALS RCS LYON 803 981 364 // AEROMETALS INDIA PRIVATE LIMITED U46909KA2025FTC209861 // ACNIS SHANGHAI // 2027 // ACNIS DO BRASIL CNPJ 09429367000108